



Roucke TFM Performance Standards

PROPERTIES	NEMA TEST #	UNIT OF MEASURE	ROUCKE TFM	NEMA LDS-2000
Light Resistance	3.3		No to Slight Effect	Slight Effect
Stain Resistance 1-10	3.4		No Effect	
Stain Resistance 11-15	3.4		Slight to Moderate Effect	
Resistance to Surface Wear	3.1	Cycles	Solids 400 Prints 100	
Chemical Resistance/Cleanability	N/A		Highly Resistant to Common Cleaning Agents, Weak Acids and Alkalis	N/A
Scratch Resistance (See Note 1)	N/A	Newtons	Minimum 2.0	N/A
Ball Impact Resistance	3.8	Inches	(See Note 2)	15 (VGL)
Boiling Water	3.5		No to Slight Effect	No to Slight Effect

- 1 Scratch Resistance Test in accordance with European Standard EN438
- 2 Using a specialized resin system and 3/4" thick board having a density of 45 lb., NEMA standard of 15 inches is achieved